

Viking HD HZ test results

CHEMICAL	PERMEATION BT* TIME (MINUTES)			EN 14225-2 PROTECTION INDEX
	MATERIAL	SEAM	ZIPPER	
Sulphuric acid,H2 SO4 (aqueous)	> 480	> 480	> 480	High
Sodium Hydroxide, NaOH 50% (aqueous)	> 480	> 480	> 480	High
Isopropanol	> 480	> 480	> 480	High
Toluene 0.05% (aqueous)	> 480	> 480	> 480	High
Liquid B	42	38	48	Low/Low
Liquid F	309	135	> 480	High

CLASSIFICATION OF RESULTS:

Minimum breakthrough time required : 20 minutes

Low protection index : 20 - 60 minutes

High protection index : > 60 minutes