

Viking PROTECH/COMBAT BE Navy HZ test results**WITH HD ZIPPER FITTED**

CHEMICAL	PERMEATION BT* TIME (MINUTES)			EN 14225-2 PROTECTION INDEX
	MATERIAL	SEAM	ZIPPER	
Sulphuric acid , H2 SO4 (aqueous)	> 480	> 480	> 480	High
Sodium Hydroxide, NaOH, 50% (aqueous)	> 480	> 480	> 480	High
Isoproponal	> 480	> 480	> 480	High
Toluene 0.05% (aqueous)	> 480	> 480	> 480	High
Liquid B	48	32	48	Low
Liquid F	355	121	> 480	High

CLASSIFICATION OF RESULTS:**Minimum breakthrough time required : 20 minutes****Low protection index : 20 - 60 minutes****High protection index : > 60 minutes**